

Polyrocks 7001C

Acrylonitrile Butadiene Styrene

Polyrocks Chemical Co., Ltd

Message:

7001(+) is environmental flame retardant ABS with environmental bromine-antimony flame retardant system. Adopting the advanced processing technology to ensure flame ratardant effect and have good rigidity and toughness. Environmental flame retardant ABS has passed SGS, CTI tests, and meets the requirements of RoHS, SVHC, PFOS & PFOA, 16P, PAHs...etc.

Flame retardant ABS7001C: good toughness, excellent flowability, high temperature resistance, excellent glossiness.

Application: High-end electronic appliances panels, frame, keyboard, LED front side outer, base...etc.

General Information			
Additive	Flame retardancy 2		
Features	Good Rigidity		
	Highlight		
	High liquidity		
	Heat resistance, high		
	Good toughness		
	Flame retardancy		
Uses	LEDs		
	Electrical/Electronic Applications		
	Home appliance components		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
Forms	Particles		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.18	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	75	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	50.0	MPa	ASTM D638
Tensile Elongation (Break)	25	%	ASTM D638
Flexural Modulus	2500	MPa	ASTM D790
Flexural Strength	65.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	150	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	95.0	°C	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.5 mm	V-0		UL 94

2.0 mm	V-0	UL 94
3.0 mm	5VA	UL 94
Glow Wire Flammability Index	850	°C IEC 60695-2-12

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

