

Tenite™ Acetate 105E1R26033 Clear, Trsp

Cellulose Acetate
Eastman Chemical Company

Message:

Tenite™ cellulosic plastics are noted for their excellent balance of properties - toughness, hardness, strength, surface gloss, clarity, and a warm feel. The mechanical properties of Tenite™ cellulosic plastics differ with plasticizer levels. Lower plasticizer content yields a harder surface, higher heat resistance, greater rigidity, higher tensile strength, and better dimensional stability. Higher plasticizer content increases impact strength. Tenite™ cellulosic plastics are available in natural, clear, amber, and black. Color concentrates are available in let-down ratios from 10:1 to 40:1. Tenite™ Cellulose Acetate 105-33 is heat stabilized and has a plasticizer level of 33%.

General Information			
Additive	Heat Stabilizer		
	Plasticizer (33%)		
Features	Good Strength		
	Good Toughness		
	Heat Stabilized		
	High Gloss		
	High Hardness		
	Plasticized		
	Renewable Resource Content		
	Soft		
Uses	Cosmetics		
	Decorative Parts		
	Eyeglasses		
	Handles		
	Sporting Goods		
	Toys		
Appearance	Amber		
	Black		
	Clear/Transparent		
	Natural Color		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.27	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.20 to 0.60	%	ASTM D955
Water Absorption (23°C, 24 hr)	2.3	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method

Rockwell Hardness (R-Scale, 23°C)	59		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 23°C	26.2	MPa	
Break, 23°C	29.6	MPa	
Tensile Elongation (Break, 23°C)	30	%	ASTM D638
Flexural Modulus (23°C)	1660	MPa	ASTM D790
Flexural Strength (Yield, 23°C)	40.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-40°C	53	J/m	
23°C	220	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load ¹			ASTM D648
0.45 MPa, Annealed	74.0	°C	
1.8 MPa, Annealed	63.0	°C	
Vicat Softening Temperature ²	100	°C	ASTM D1525
CLTE - Flow (23°C)	2.0E-5	cm/cm/°C	ASTM D696
Specific Heat (23°C)	1260 to 1670	J/kg/°C	DSC
Thermal Conductivity ³ (23°C)	0.25	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength (23°C)	12 to 19	kV/mm	ASTM D149
Dielectric Constant (23°C, 1 MHz)	3.30 to 3.80		ASTM D150
Dissipation Factor (23°C, 1 MHz)	0.010 to 0.15		ASTM D150
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.460 to 1.490		ASTM D542
Transmittance (1520 μm)	> 90.0	%	ASTM E308
Haze (1520 μm)	< 8.5	%	ASTM D1003
Additional Information	Nominal Value	Unit	Test Method
Soluble Matter Loss (23°C)	0.60	%	ASTM D570
Weight Loss on Heating - 72 hrs (80°C)	3.6	%	ASTM D706
NOTE			
1.	Conditioned 4 hours at 70°C (158°F)		
2.	Conditioned 4 hours at 70°C (158°F)		
3.	Range: 0.17 to 0.33		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

