

Evolve™ SP2320

Linear Low Density Polyethylene

Prime Polymer Co., Ltd.

Message:

Evolve™ SP2320 is a Linear Low Density Polyethylene product. It can be processed by blown film and is available in Asia Pacific, Europe, or North America. Applications of Evolve™ SP2320 include agricultural, coating applications, film and industrial applications.

Characteristics include:

- Clarity
- Fast Molding Cycle
- Good Sealability

General Information			
Features	Fast Molding Cycle		
	High Clarity		
	Low Temperature Heat Sealability		
Uses	Agricultural Applications		
	Film		
	Industrial Applications		
	Laminates		
Processing Method	Blown Film		
Physical	Nominal Value	Unit	Test Method
Density	0.920	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.9	g/10 min	ISO 1133
Environmental Stress-Cracking Resistance	> 1000	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, Injection Molded)	55		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break, Injection Molded)	19.0	MPa	ISO 527-2
Tensile Strain (Break, Injection Molded)	350	%	ISO 527-2
Flexural Modulus (Injection Molded)	240	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	101	°C	ISO 306
Melting Temperature	118	°C	ISO 11357-3

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT