

BCC Resins BC 7062-2H

Epoxy; Epoxide
BCC Products Inc.

Message:

BC 7062 are aluminum filled, low viscosity epoxy mass casting resins. These room temperature cure systems allow the user choice thicknesses of 1/8 inch to a maximum of 6 inches without foaming or yielding excessive shrinkage. Casting thicknesses may be increased by incorporating aluminum needles, puffs or granules. BC 7062, when properly cured, provides nearly perfect reproduction, resulting in a dimensionally stable, hard, tough surface. For use in constructing duplicate models, prototypes, patterns, facing dies, etc.

General Information			
Filler / Reinforcement	Aluminum		
Features	Good Dimensional Stability		
	Good Toughness		
	High Hardness		
	Low Viscosity		
Uses	Modeling Material		
	Molds/Dies/Tools		
	Prototyping		
Appearance	Silver		
Forms	Liquid		
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
Hardener	Mix Ratio by Weight: 1.0, Mix Ratio by Volume: 1.0		
Resin	Mix Ratio by Weight: 9.0, Mix Ratio by Volume: 4.6		
Pot Life ¹ (24°C)	70 to 80	min	ASTM D2393
Thermoset Mix Viscosity ² (24°C)	7000	cP	
Demold Time	1400 to 1800	min	
Post Cure Time			
24°C	120	hr	
66°C	3.0 to 4.0	hr	
Additional Information	Nominal Value	Unit	Test Method
Casting Thickness	0.750 to 2.00		
NOTE			
1.	2 lb mass		
2.	Brooksfield		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

