

Huaфон HF-1175AP

Thermoplastic Polyurethane Elastomer (Polyester)

Huaфон Group Co., Ltd.

Message:

Operation: Injection molding
Characteristics: Easy processing, Fast de-molding
Applications: Gardening shoes, Accessories, Fashion shoe sole, etc., Heel life.

General Information			
Features	Good Processability		
Uses	Footwear		
Processing Method	Injection Molding		
Hardness	Nominal Value	Test Method	
Durometer Hardness (Shore A)	76	ASTM D2240	
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	5.60	MPa	ASTM D412
Tensile Strength	18.0	MPa	ASTM D412
Tensile Elongation (Break)	550	%	ASTM D412
Tear Strength	96.0	kN/m	ASTM D624

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT