

Chemiton NA H8NA 70

Styrene Ethylene Butylene Styrene Block Copolymer
Franplast S.r.l.

Message:

SEBS based compound, ideal for blow moulding processing. Its main characteristics are good recovery and opaque appearance. It is ideal for the production of flasks for cosmetics.

Application:
Soap-dish

General Information			
Uses	Cosmetics		
	Household Goods		
Appearance	Opaque		
Processing Method	Blow Molding		
	Injection Molding		

Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	30	g/10 min	ASTM D1238

Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	70		ISO 868

Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	9.00	MPa	ISO 527-2
Nominal Tensile Strain at Break	850	%	ISO 527-2

Elastomers	Nominal Value	Unit	Test Method
Tear Strength	28	kN/m	ISO 34-1

Thermal	Nominal Value	Unit	
Service Temperature	-30 to 80	°C	

Injection	Nominal Value	Unit	
Drying Time	0.0	hr	
Rear Temperature	135 to 165	°C	
Middle Temperature	140 to 170	°C	
Front Temperature	145 to 175	°C	
Nozzle Temperature	155 to 185	°C	
Mold Temperature	< 25.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

