

Elvax® 250

Ethylene Vinyl Acetate Copolymer
DuPont Packaging & Industrial Polymers

Message:

DuPont™ Elvax® 250 is an ethylene-vinyl acetate copolymer resin for use in industrial applications.

Composition

28 % By Weight Vinyl Acetate comonomer content

Thermal Stabilizer: BHT antioxidant

Applications

Elvax® resins can be used in a variety of applications involving molding, compounding, extrusion, adhesives, sealants, and wax blends. For additional information and properties associated with specific applications, please refer to the Grade Selector Guides found on the Elvax® website for industrial applications. http://www2.dupont.com/Elvax/en_US/tech_info/index.html

General Information	
Additive	Antioxidant Heat Stabilizer
Features	Antioxidant Copolymer Food Contact Acceptable Heat Stabilized
Uses	Adhesives Blending Compounding Industrial Applications Sealants Wire Jacketing
Agency Ratings	FDA 21 CFR 177.1350(a)(1)
Forms	Pellets
Processing Method	Blow Molding Compounding Compression Molding Extrusion Foam Processing Injection Molding Sheet Extrusion Structural Foam Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.950	g/cm ³	ASTM D792, ISO 1183

Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	25	g/10 min	ASTM D1238, ISO 1133
Vinyl Acetate Content	28.0	wt%	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	42.0	°C	ASTM D1525, ISO 306
Peak Melting Temperature	70.0	°C	ASTM D3418, ISO 3146
Injection	Nominal Value	Unit	
Processing (Melt) Temp	< 230	°C	
Extrusion	Nominal Value	Unit	
Melt Temperature	< 230	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

