Hostacom TRC 411N C11547

Polypropylene Copolymer

LyondellBasell Industries

Message:

Hostacom TRC 411N is a 15% talc filled PP copolymer compound with high flowability, good impact/stiffness balance and excellent scratch resistance, offering low odour and low emissions performances.

This product is also available in other colors, new colors can be developed depending on customer requirements.

For regulatory compliance information, see Hostacom TRC 411N C11547 Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

General Information					
Filler / Reinforcement	Talc filler, 15% filler by weight				
Features	Low volatilization				
	Low density				
	Rigid, good				
	Impact resistance, high				
	Good UV resistance				
	Workability, good				
	Good color stability				
	Good wear resistance				
	High liquidity				
	Low temperature impact resistance				
	Scratch resistance				
	The smell is low to none				
	Good appearance				
	ductility				
	Excellent appearance				
Uses	Application in Automobile Field				
	Car interior parts				
	Car dashboard				
Appearance	Available colors				
Processing Method	Injection molding				
Physical	Nominal Value	Unit	Test Method		
Density (23°C)	1.02	g/cm ³	ISO 1183/A		
Melt Mass-Flow Rate (MFR) (230°C/2.16					
kg)	19	g/10 min	ISO 1133		
Mechanical	Nominal Value	Unit	Test Method		
Flexural Modulus ¹ (23°C)	1800	MPa	ISO 178/A		
Impact	Nominal Value	Unit	Test Method		
Charpy Notched Impact Strength (23°C)	30	kJ/m²	ISO 179/1eA		

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	90.0	°C	ISO 75-2/B
NOTE			
1.	1.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

