

# EMAC+® SP1305

Ethylene Methyl Acrylate Copolymer

Westlake Chemical Corporation

## Message:

EMAC resins adhere to and are compatible with a wide range of materials including paper, polyolefins, oriented polyolefins, polyesters, ionomers, PVdC, unplasticized PVC and other polar polymers. For use as heat seal layer, adhesive layer, or modifier for cost/performance enhancement. They are soft, pliable and tough at ambient and freezing temperatures and exhibit excellent ESCR. These polymers exhibit high solids fillability and compatibility with a wide range of polymers. This facilitates their uses as bases for all-purpose concentrates for addition to a wide spectrum of polymers. EMAC resins process like LDPE. EMAC+ Specialty Copolymers are produced under patented technology: US Patent 5804675.

General Information			
Features	Good Adhesion		
	Good Flexibility		
	Good Heat Seal		
	Good Toughness		
	High ESCR (Stress Crack Resist.)		
	Soft		
Uses	Film		
	Tie-Layer		
Physical	Nominal Value	Unit	Test Method
Density	0.942	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Methyl Acrylate Content	20.0	wt%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	37		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Break)	11.0	MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Break)	820	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -73.0	°C	ASTM D746
Vicat Softening Temperature	50.0	°C	ASTM D1525
Peak Melting Temperature	96.0	°C	ASTM D3418
NOTE			
1.	Type IV, 500 mm/min		
2.	Type IV, 500 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

