

Kepital® TE-14

Acetal (POM) Copolymer

Korea Engineering Plastics Co., Ltd

Message:

Kepital® TE-14 is an Acetal (POM) Copolymer material. It is available in Asia Pacific, Europe, or North America.

Important attributes of Kepital® TE-14 are:

- Chemical Resistant
- Creep Resistant
- Fatigue Resistant
- Good Dimensional Stability
- Good Processability
- Typical applications include:
 - Engineering/Industrial Parts
 - Electrical/Electronic Applications
 - Automotive
 - Caps/Lids/Closures

General Information			
Additive	Lubricant		
Features	Fatigue Resistant		
	Good Chemical Resistance		
	Good Creep Resistance		
	Good Dimensional Stability		
	Good Impact Resistance		
	Good Moldability		
	Good Thermal Stability		
	Good Toughness		
	Good Wear Resistance		
	Good Weather Resistance		
	High Viscosity		
	Low Friction		
	Lubricated		
Uses	Automotive Applications		
	Caps		
	Electrical Parts		
	Electronic Data Processing		
	Fasteners		
	Industrial Parts		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.36	g/cm ³	ASTM D792

Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.7	%	ASTM D955
Water Absorption (24 hr)	0.28	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	38.3	MPa	ASTM D638
Flexural Modulus	1320	MPa	ASTM D790
Flexural Strength	47.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	200	J/m	ASTM D256
Tensile Impact Strength (1.60 mm)	254	kJ/m ²	ASTM D1822
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	140	°C	
1.8 MPa, Unannealed	87.8	°C	
Melting Temperature	165	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

