

Nanjing Hongrui PA66 A401

Polyamide 66

Nanjing Hongrui Engineering Plastics Co., Ltd.

Message:

Nanjing Hongrui PA66 A401 is a Polyamide 66 (Nylon 66) material. It is available in Asia Pacific.

Important attributes of Nanjing Hongrui PA66 A401 are:

Flame Rated

Good Toughness

Impact Resistant

Typical applications include:

Plumbing/Piping/Potable Water

Sporting Goods

General Information	
---------------------	--

Features	Good Toughness
	High Impact Resistance
Uses	Piping
	Sporting Goods

Physical	Nominal Value	Unit	Test Method
----------	---------------	------	-------------

Specific Gravity	1.09	g/cm ³	ASTM D792
------------------	------	-------------------	-----------

Molding Shrinkage - Flow	1.5	%	ASTM D955
--------------------------	-----	---	-----------

Hardness	Nominal Value	Unit	Test Method
----------	---------------	------	-------------

Rockwell Hardness (R-Scale)	113		ASTM D785
-----------------------------	-----	--	-----------

Mechanical	Nominal Value	Unit	Test Method
------------	---------------	------	-------------

Tensile Strength	60.0	MPa	ASTM D638
------------------	------	-----	-----------

Tensile Elongation (Break)	10	%	ASTM D638
----------------------------	----	---	-----------

Flexural Modulus	2000	MPa	ASTM D790
------------------	------	-----	-----------

Flexural Strength	70.0	MPa	ASTM D790
-------------------	------	-----	-----------

Impact	Nominal Value	Unit	Test Method
--------	---------------	------	-------------

Notched Izod Impact (Area)	12.0	kJ/m ²	ASTM D256
----------------------------	------	-------------------	-----------

Thermal	Nominal Value	Unit	Test Method
---------	---------------	------	-------------

Deflection Temperature Under Load (0.45 MPa, Unannealed)	200	°C	ASTM D648
--	-----	----	-----------

Melting Temperature	260	°C	
---------------------	-----	----	--

Electrical	Nominal Value	Unit	Test Method
------------	---------------	------	-------------

Surface Resistivity	1.0E+13	ohms	ASTM D257
---------------------	---------	------	-----------

Dielectric Strength	20	kV/mm	ASTM D149
---------------------	----	-------	-----------

Flammability	Nominal Value	Unit	Test Method
--------------	---------------	------	-------------

Flame Rating	HB		UL 94
--------------	----	--	-------

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

