

Telcar® GS6035

Thermoplastic Elastomer

Teknor Apex Asia Pacific PTE. LTD.

Message:

Telcar®GS6035 is a thermoplastic elastomer (TPE) material. This product is available in the Asia-Pacific region.

General Information			
UL YellowCard	E142591-100423019		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.988	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/2.16 kg)	11	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	60		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% strain	3.00	MPa	ASTM D412
300% strain	4.00	MPa	ASTM D412
Tensile Strength (Yield)	8.00	MPa	ASTM D412
Tensile Elongation (Break)	570	%	ASTM D412
Additional Information			
Item Code (Reference): 9504224			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT