

Iupilon® EFT3200

Polycarbonate

Mitsubishi Engineering-Plastics Corp

Message:

Iupilon® EFT3200 is a polycarbonate (PC) material. This product is available in North America, Europe or Asia Pacific region. The processing method is injection molding.

Iupilon® The main features of the EFT3200 are:

flame retardant/rated flame

Flame Retardant

Halogen-free

General Information			
UL YellowCard	E41179-472329		
Additive	Flame retardancy		
Features	Phosphorus content, low (to none)		
	Bromine-free		
	Flame retardancy		
Appearance	Clear/transparent		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	7.0	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	8.00	cm ³ /10min	ISO 1133
Molding Shrinkage			
Vertical flow direction: 3.20mm	0.50 - 0.70	%	
Flow direction: 3.20mm	0.50 - 0.70	%	
Water Absorption (Saturation, 23°C)	0.24	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2400	MPa	ISO 527-2
Tensile Stress (Yield)	62.0	MPa	ISO 527-2
Tensile Strain (Yield)	6.5	%	ISO 527-2
Nominal Tensile Strain at Break	100	%	ISO 527-2
Flexural Modulus	2400	MPa	ISO 178
Flexural Stress	93.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	16	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			

0.45 MPa, not annealed	136	°C	ISO 75-2/B
1.8 MPa, not annealed	124	°C	ISO 75-2/A
Linear thermal expansion coefficient			ISO 11359-2
Flow	6.5E-5	cm/cm/°C	ISO 11359-2
Lateral	6.6E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	6.0E+15	ohms	IEC 60093
Volume Resistivity	3.0E+16	ohms·cm	IEC 60093
Comparative Tracking Index (CTI)	PLC 3		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (2.00 mm)	V-0		UL 94
Additional Information			
EFT3200U : UV Stabilized			
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 90.0	°C	
Drying Time	4.0 - 8.0	hr	
Rear Temperature	270 - 290	°C	
Middle Temperature	280 - 300	°C	
Front Temperature	280 - 310	°C	
Nozzle Temperature	280 - 310	°C	
Mold Temperature	70.0 - 100	°C	
Injection Pressure	50.0 - 150	MPa	
Screw Speed	50 - 100	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT