## Tecnoprene® VK6 HIT1 NERO900

Polypropylene Homopolymer SO.F.TER. SPA

## Message:

High fluidity polypropylene homopolymer reinforced with 31% chemically coupled glass fiber, high heat stabilization

General Information			
Filler / Reinforcement	Glass Fiber,31% Filler by Weight		
Additive	Heat Stabilizer		
Features	Chemically Coupled		
	Heat Stabilized		
	High Flow		
	Homopolymer		
Agency Ratings	EC 1907/2006 (REACH)		
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	13	g/10 min	ASTM D1238
Molding Shrinkage	0.20	%	Internal Method
Water Absorption (Saturation, 23°C)	0.020	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	6400	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	120	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8			
MPa, Unannealed)	148	°C	ASTM D648
Vicat Softening Temperature	137	°C	ASTM D1525 <sup>1</sup>
Flammability	Nominal Value		Test Method
Flame Rating (3.20 mm)	НВ		UL 94
NOTE			
1.	Rate A (50°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

