

Chiao Fu PA66/6 MB212G33 NAT

Polyamide 66/6 Copolymer
Chiao Fu Enterprises Co., Ltd.

Message:

Chiao Fu PA66/6 MB212G33 NAT is a Polyamide 66/6 Copolymer (Nylon 66/6) product filled with 33% glass fiber. It is available in Asia Pacific, Europe, or North America.
Characteristics include:
Flame Rated
RoHS Compliant

General Information			
Filler / Reinforcement	Glass Fiber,33% Filler by Weight		
RoHS Compliance	RoHS Compliant		
UL File Number	E135541		
Appearance	Natural Color		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.39	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (235°C/2.16 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow	< 0.25	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	167	MPa	ASTM D638
Tensile Elongation (Break)	< 5.0	%	ASTM D638
Flexural Modulus	7450	MPa	ASTM D790
Flexural Strength	245	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	160	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	215	°C	ASTM D648
RTI Elec	65.0	°C	UL 746
RTI Imp	65.0	°C	UL 746
RTI Str	65.0	°C	UL 746
Flammability	Nominal Value	Test Method	
Flame Rating			UL 94
1.50 mm, All	HB		
3.00 mm, All	HB		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

