

MAJORIS DT300E - 9432

High Density Polyethylene

AD majoris

Message:

DT300E - 9432 is a 30% mineral filled polyethylene high density compound intended for injection moulding.

The product is available in black DT300E - 8229) and natural (DT300E) but other colours can be provided on request.

APPLICATIONS

DT300E - 9432 is intended for components which require rigidity and dimensional stability.

Suitable applications are:

Electrical tool and appliance components

Miscellaneous automotive technical items

Technical components

General Information			
Filler / Reinforcement	Mineral filler, 30% filler by weight		
Features	Good dimensional stability		
	High density		
	Recyclable materials		
	Medium hardness		
Uses	Electrical/Electronic Applications		
	Power/other tools		
	Home appliance components		
	Application in Automobile Field		
Appearance	Black		
	Available colors		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.19	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	9.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3300	MPa	ISO 527-2/1
Tensile Stress (Break)	28.0	MPa	ISO 527-2/50
Flexural Modulus ¹	2150	MPa	ISO 178
Flexural Stress	46.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	42	kJ/m ²	ISO 179/1eU

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	112	°C	ISO 75-2/B
1.8 MPa, not annealed	66.0	°C	ISO 75-2/A
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Rear Temperature	180 - 200	°C	
Processing (Melt) Temp	190 - 230	°C	
Mold Temperature	30.0 - 50.0	°C	
Injection Rate	Moderate		
Injection instructions			
Holding pressure: 50 to 70% of the injection pressure			
NOTE			
1.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT