

# NuSil CF1-3800

Silicone

NuSil Technology

Message:

The Aircraft Industry has used silicone adhesives and coatings for over five decades. Silicone's ability to maintain its elasticity and low modulus over a broad temperature range provides excellent utility in extreme environments. Recent advances in material technology provide more opportunities for the Aircraft engineer in choosing the best material for an intended application. Examples of NuSil's capabilities in custom silicones for Aircraft are demonstrated in the following sections.

Fuel Resistance

Static Dissipation and Electrically Conductive Silicones

Ice-Phobic Coatings

Comment: Thermally Conductive 1.25 W/m-K, Fuel Resistance

General Information			
Features	Electrically Conductive		
	Fuel Resistant		
	Thermally Conductive		
Uses	Aircraft Applications		
	Electrical/Electronic Applications		
Thermal	Nominal Value	Unit	Test Method
Thermal Conductivity	1.3	W/m/K	ASTM C177
Thermoset	Nominal Value	Unit	
Thermoset Components			
Part A	Mix Ratio by Weight: 15		
Part B	Mix Ratio by Weight: 1.0		
Additional Information	Nominal Value	Unit	
Cure System	Platinum		
Operating Temperature	-50 to 200	°C	
Uncured Properties	Nominal Value	Unit	
Color	White		
Density	1.53	g/cm <sup>3</sup>	
Curing Time (150°C)	0.50	hr	
Pot Life	90	min	
Cured Properties	Nominal Value	Unit	
Shore Hardness (Shore A)	50		
Tensile Strength	0.862	MPa	
Tensile Elongation at Break	50	%	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT