

Formolon® 25

Polyvinyl Chloride Homopolymer

Formosa Plastics Corporation, U.S.A.

Message:

F-25 is a medium molecular weight PVC homopolymer dispersion resin with low residual surfactant content. Applications include caulk and sealants.

General Information			
Features	Homopolymer		
	Low Residuals		
	Medium Molecular Weight		
Uses	Sealants		
Agency Ratings	EC 1907/2006 (REACH)		
Physical	Nominal Value		Test Method
K-Value	73.0		
Inherent Viscosity	1.1		ASTM D1243
Relative Viscosity	2.55		
Brookfield Viscosity			
-- ¹	42.0	Pa·s	
-- ²	160	Pa·s	
Sever Viscosity ³	18.1	Pa·s	
Gel Temperature	71	°C	
Methanol Extractables	1.0	%	ASTM D2222
Volatiles	0.10	%	ASTM D3030
NOTE			
1.	20 rpm, aged 2 hr		
2.	2 rpm, aged 2 hr		
3.	100 psig, aged 2 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT