

ARMAMID® PA HC 30-1AF

Polyamide 6

Poly Plastic

Message:

ARMAMID® PA HC 30-1AF is a Polyamide 6 (Nylon 6) product. It is available in Europe.

General Information		
Physical	Nominal Value	Unit
Density	1.22	g/cm ³
Molding Shrinkage	0.40 to 0.50	%
Mechanical	Nominal Value	Unit
Tensile Stress (Yield)	135	MPa
Flexural Modulus (23°C)	11000	MPa
Flexural Stress	200	MPa
Impact	Nominal Value	Unit
Charpy Unnotched Impact Strength (20°C)	25	kJ/m ²
Thermal	Nominal Value	Unit
Melting Temperature	218	°C
Heat Stability - of wick	209	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT