

# ELITE™ 5815P

Enhanced Polyethylene Resin

The Dow Chemical Company

### Message:

ELITE™ 5815P is produced via INSITE™ Technology from Dow. It is an ethylene alpha-olefin resin for monolayer and coextrusion coating that offers excellent low temperature seal initiation, ultimate seal strength, hot tack strength and good taste and odor performance.

Monolayer and coextrusion coating for packaging applications.

Coextruded with PRIMACOR™ copolymer as a cost effective foil or PET sealant.

Complies with U.S. FDA FCN 424

Complies with EU. No 10/2011

Consult the regulations for complete details.

General Information			
Agency Ratings	FDA FCN 424		
	Europe No 10/2011		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.910	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	15	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Seal Initiation Temperature <sup>1</sup>	90.6	°C	Internal method
Thermal	Nominal Value	Unit	Test Method
Melting Temperature (DSC)	124	°C	Internal method
Extrusion	Nominal Value	Unit	Test Method
Melt Temperature	260 - 316	°C	
Neck-in (316°C, 25.4 µm)	235.0	mm	Internal method
Minimum coating thickness		µm	Internal method
Minimum coating weight		g/m <sup>2</sup>	Internal method
Extrusion instructions			
吹塑薄膜的制造条件: 挤塑机:Black Clawson 螺杆尺寸:3.5 英寸 (90 mm);30:1 L/D 模具间隙:20 密尔 (0.508 mm) 冷却辊温度:57°F (14°C) 熔体温度:600°F (315°C) 输出:250 磅/小时 气隙:6 英寸 (150 mm)			
NOTE			

- Coating onto PET/poly/foil/0.5 mil PRIMACOR- Temperature at which 1 lb/in (4.4 FN/25.4 mm) heat seal strength is achieved.- Heat Seal Strength, Topwave HT Tester, 0.5 S dwell, 40 psi bar pressure, 10 in/min pull speed.

1.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

