

Teflon® FEP CJ 95

Perfluoroethylene Propylene Copolymer

DuPont Fluoropolymers

Message:

For inventory control purposes product name may be followed by an X.
Products labeled FEP CJ 95 and FEP CJ 95 X are equivalent and all information in this document is applicable to both.

Typical Application
Insulation and jacket for Wire and Cable, in applications demanding a high degree of stress crack resistance. Tubes and piping for general and chemical process industry.

DuPont Teflon ® FEP CJ 95 is a melt-processible copolymer of tetrafluoroethylene and hexafluoropropylene without additives that meets the requirements of ASTM D 2116 type I.

It offers the excellent combination of properties characteristic of Teflon ® fluoropolymer resins: non-ageing characteristics, chemical inertness, exceptional dielectric properties, low flammability, heat resistance, toughness and flexibility, low coefficient of friction, non-stick characteristics, negligible moisture absorption and excellent weather resistance. As an intermediate molecular weight resin Teflon ® FEP CJ 95 offers higher processing speeds than many FEP grades with similar high level of stress crack resistance.

Stress crack resistance is an important element in establishing end-use performance. Extensive testing of wire and cable constructions is required for definitive performance evaluation. Experience shows that the MIT folding endurance or flex life test, performed on a thin film of resin, has established a good correlation with extensive cable testing. The higher the MIT flex life, the higher the stress-crack resistance of the resin. MIT test results should be viewed as a guide to comparative performance of the various grades of resin. We recommend that for applications involving repeated thermal and flex cycling, specific tests on the final cable always should be undertaken. See also DuPont's bulletin "Grade selector for Wire and Cable applications".

General Information	
UL YellowCard	E54681-557110
Features	Food Contact Acceptable
	Good Chemical Resistance
	Good Flexibility
	Good Toughness
	Good Weather Resistance
	High ESCR (Stress Crack Resist.)
	High Heat Resistance
	Low Friction
	Low Moisture Absorption
Uses	Cable Jacketing
	Insulation
	Wire & Cable Applications
Agency Ratings	ASTM D 2116 type 1
	EU 10/2011
	FDA 21 CFR 177.1550
Forms	Pellets
Processing Method	Blow Molding
	Compression Molding

Extrusion
Injection Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	2.13	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (372°C/5.0 kg)	5.0	g/10 min	ASTM D2116, ISO 12086
Water Absorption (24 hr)	< 0.010	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	56		ASTM D2240, ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	28.0	MPa	ASTM D638, ISO 12086
Tensile Elongation (Break, 23°C)	330	%	ASTM D638, ISO 12086
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	No Break		ASTM D256, ISO 180
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature ¹	205	°C	
Melting Temperature ²	260	°C	
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength			
0.250 mm ³	> 95	kV/mm	ASTM D149
0.250 mm	> 95	kV/mm	IEC 60243-1
Dielectric Constant			ASTM D150, IEC 60250
1 kHz	2.03		
1.00 GHz	2.03		
Dissipation Factor			ASTM D150, IEC 60250
1 kHz	5.0E-5		
1.00 GHz	8.0E-4		
Flammability	Nominal Value	Unit	Test Method
Flame Rating ⁴	V-0		UL 94
Oxygen Index	> 95	%	ASTM D2863, ISO 4589-2
Additional Information	Nominal Value	Unit	Test Method
Critical Shear Rate (372°C)	20.0	sec ⁻¹	Internal Method
Guide DDR Range			
for cable extrusion	20.0 to 120		
for tubing extrusion	3.00 to 8.00		
MIT Folding Endurance - film (200.0 µm)	4.0E+4	Cycles	ASTM D2176
NOTE			

1.	The continuous service temperature is based on accelerated heat-aging tests, and represents the temperature at which tensile strength and ultimate elongation retains 50% of the original values, after 20 000 h thermal aging When considering the use of Teflon ® FEP at elevated temperatures especially in combination with mechanical, electrical or chemical exposure, preliminary testing should be done to verify suitability.
2.	ASTM D4591 / D3418
3.	Method A (Short-Time)
4.	- These results are based on laboratory tests, under controlled conditions, and do not reflect performance under actual fire conditions.- Current rating is a typical theoretical value

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT