

TOTAL Polypropylene PPC 7642

Polypropylene Impact Copolymer

TOTAL Refining & Chemicals

Message:

Polypropylene PPC 7642 is a nucleated and antistatic heterophasic copolymer with a Melt Flow Index of 16 g/10 min.
Polypropylene PPC 7642 is characterized by a very high stiffness.
Polypropylene PPC 7642 has been developed for a wide range of injection moulding applications including battery cases, electrical appliance housings, toys, closures and lids.

General Information			
Additive	Nucleating Agent		
Features	High Stiffness		
	Nucleated		
Uses	Appliances		
	Battery Cases		
	Closures		
	Electrical Housing		
	Lids		
	Toys		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.905	g/cm ³	ISO 1183
Apparent Density	0.53	g/cm ³	ISO 60
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	16	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	90		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1600	MPa	ISO 527-2
Tensile Stress (Yield)	27.0	MPa	ISO 527-2
Tensile Strain (Yield)	5.0	%	ISO 527-2
Flexural Modulus	1500	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-20°C	5.0	kJ/m ²	
23°C	9.0	kJ/m ²	

Notched Izod Impact Strength			ISO 180
-20°C	5.0	kJ/m ²	
23°C	8.0	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	95.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	53.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	145	°C	ISO 306/A50
--	75.0	°C	ISO 306/B50
Melting Temperature (DSC)	165	°C	ISO 3146

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

