

Elastocon® OF75

Thermoplastic Elastomer
Elastocon TPE Technologies

Message:

Elastocon® OF75 is a natural thermoplastic elastomer that has been developed for applications that require oil/plasticizer free, high strength properties and a reduced coefficient of friction. Elastocon® OF75 is FDA compliant and well suited for consumer goods and industrial applications requiring U.V. stability. Elastocon® OF75 can be overmolded onto polypropylene. Elastocon® OF75 is supplied as ready to use pellets in 1000 lb. quantities.

General Information	
Features	Good UV Resistance
	High Strength
	Low Friction
Uses	Industrial Castings
	Overmolding
Appearance	Natural Color
Forms	Pellets
Processing Method	Blow Molding
	Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.927	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	75		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	4.78	MPa	ASTM D412
Tensile Strength (Yield)	11.6	MPa	ASTM D412
Tensile Elongation (Break)	590	%	ASTM D412
Injection	Nominal Value	Unit	
Rear Temperature	166 to 177	°C	
Front Temperature	182 to 188	°C	
Nozzle Temperature	193 to 204	°C	
Mold Temperature	21.1 to 37.8	°C	
Injection Rate	Fast		
Back Pressure	0.689 to 1.38	MPa	
Screw Compression Ratio	2.5:1.0 to 3.0:1.0		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

