PRL NY66-M25G15

Polyamide 66

Polymer Resources Ltd.

Message:

PRL NY66-M25G15 is a Polyamide 66 (Nylon 66) product filled with 15% glass fiber and 25% mineral. It can be processed by injection molding and is available in North America.

Characteristics include:

RoHS Compliant

Heat Resistant

Lubricated

General Information				
Filler / Reinforcement	Glass Fiber,15% Filler by Weight			
	Mineral,25% Filler by Weight			
Additive	Lubricant			
Features	High Heat Resistance			
	Lubricated			
RoHS Compliance	RoHS Compliant			
Forms	Pellets			
Processing Method	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.49	g/cm³	ASTM D792	
Molding Shrinkage - Flow (3.18 mm)	0.40 to 0.90	%	ASTM D955	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength			ASTM D638	
Yield, 3.18 mm	131	МРа		
Break, 3.18 mm	131	МРа		
Flexural Modulus (3.18 mm)	6890	МРа	ASTM D790	
Flexural Strength (3.18 mm)	179	МРа	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact (23°C, 3.18 mm)	53	J/m	ASTM D256	
Thermal	Nominal Value	Unit	Test Method	
Deflection Temperature Under Load			ASTM D648	
0.45 MPa, Unannealed, 3.18 mm	254	°C		
1.8 MPa, Unannealed, 3.18 mm	235	°C		
Injection	Nominal Value	Unit		
Drying Temperature	73.9 to 85.0	°C		
Drying Time	3.0 to 4.0	hr		
Drying Time, Maximum	8.0	hr		
Rear Temperature	271 to 282	°C		

Middle Temperature	282 to 299	°C	
Front Temperature	282 to 304	°C	
Processing (Melt) Temp	288 to 304	°C	
Mold Temperature	82.2 to 104	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

