

# ELASTOSIL® R plus 573/70 A/B

Silicone

Wacker Chemie AG

## Message:

Silicone Rubber, HTV

Ignition and Battery Cables, Cable Industry

Electrically Conductive Rolls, Printing Industry

Ignition and Battery Cables, Automotive & Transportation

Electrically Conductive Rollers, Plastics and Rubber Processing

Electrically Conductive Rollers, Printing Industry

Extrudates, Technical, Plastics and Rubber Processing

General Information			
Uses	Wire & Cable Applications		
Processing Method	Extrusion		
	Wire & Cable Extrusion		
Uncured Properties	Nominal Value	Unit	Test Method
Color	Black		
Density	1.16	g/cm <sup>3</sup>	ISO 1183
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	72		DIN 53505
Tensile Strength	6.30	MPa	DIN 53504
Tensile Elongation at Break	250	%	DIN 53504
Compression Set	33	%	DIN ISO 815-B
Tear Strength	16.0	kN/m	ASTM D624B
Volume Resistivity	1.6	ohms · cm	DIN IEC 93

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

