

LNP™ STAT-KON™ EEF42 compound

Polyether Imide

SABIC Innovative Plastics

Message:

LNP STAT-KON* EEF42 is a compound based on Polyetherimide resin containing Carbon Fiber, Glass Fiber. Added features of this material include: Electrically Conductive.

Also known as: LNP* STAT-KON* Compound ECF-1006

Product reorder name: EEF42

General Information			
Filler / Reinforcement	Glass, carbon fiber reinforced materials		
Features	Conductivity		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.46	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow: 24 hours	0.10 - 0.20	%	ASTM D955
Transverse flow: 24 hours	0.30 - 0.40	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	15900	MPa	ASTM D638
Tensile Strength (Break)	195	MPa	ASTM D638
Tensile Elongation (Break)	1.7	%	ASTM D638
Flexural Modulus	15900	MPa	ASTM D790
Flexural Strength	276	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	71	J/m	ASTM D256
Unnotched Izod Impact (23°C)	510	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	211	°C	ASTM D648
Linear thermal expansion coefficient			ASTM E831
Flow: -40 to 40°C	3.3E-5	cm/cm/°C	ASTM E831
Lateral: -40 to 40°C	2.3E-5	cm/cm/°C	ASTM E831
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+10 - 1.0E+11	ohms · cm	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	121 - 149	°C	
Drying Time	4.0 - 6.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	343 - 354	°C	
Middle Temperature	354 - 366	°C	

Front Temperature	366 - 377	°C
Processing (Melt) Temp	360 - 366	°C
Mold Temperature	121 - 149	°C
Back Pressure	0.344 - 0.689	MPa
Screw Speed	60 - 100	rpm

NOTE		
1.	50 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT