

Hanwha Total PE 6220F

Linear Low Density Polyethylene
HANWHA TOTAL PETROCHEMICALS Co., Ltd.

Message:

6220F is a linear low-density polyethylene hexene comonomer resin for agricultural films and heavy-duty packaging films. 6220F is often used as a blending component in greenhouse film. This grade is designed to be processed in conventional blown film equipment.

General Information			
Features	Good Heat Seal		
	Good Processability		
	Good Weather Resistance		
	Hexene Comonomer		
	High Impact Resistance		
	High Tensile Strength		
	Low Density		
	Opticals		
	Puncture Resistant		
Uses	Agricultural Applications		
	Blending		
	Film		
	Packaging		
Forms	Pellets		
Processing Method	Blown Film		
Physical	Nominal Value	Unit	Test Method
Density	0.921	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.90	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	38	µm	ASTM D882
Tensile Strength			
MD : Yield,38 µm	11.8	MPa	
TD : Yield,38 µm	10.8	MPa	
MD : Break, 38 µm	42.2	MPa	ASTM D882
TD : Break, 38 µm	34.3	MPa	
Tensile Elongation			
MD : Break, 38 µm	580	%	
TD : Break, 38 µm	760	%	ASTM D1922
Elmendorf Tear Strength			
MD : 25 µm	270	g	


TD : 25 μm	520	g	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	102	°C	ASTM D1525 ¹
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 38.0 μm)	55		ASTM D2457
Haze (38.0 μm)	12	%	ASTM D1003
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	180 to 200	°C	
Cylinder Zone 2 Temp.	180 to 200	°C	
Cylinder Zone 3 Temp.	180 to 200	°C	
Cylinder Zone 4 Temp.	180 to 200	°C	
Cylinder Zone 5 Temp.	180 to 200	°C	
Die Temperature	200 to 210	°C	
NOTE			
1.	Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT