

Novalloy-X X7203L (Type V)

Polycarbonate + Styrenic

Daicel Polymer Ltd.

Message:

Novalloy-X X7203L (Type V) is a Polycarbonate + Styrenic (PC+Styrenic) material. It is available in Asia Pacific. Primary attribute of Novalloy-X X7203L (Type V): Flame Rated.

General Information			
Physical	Nominal Value	Unit	Test Method
Density	1.17	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	40	g/10 min	ISO 1133
Molding Shrinkage - Flow	0.40 to 0.60	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.30	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	53.0	MPa	ISO 527-2
Flexural Modulus	2600	MPa	ISO 178
Flexural Stress	84.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	20	kJ/m ²	ISO 179/1eA
Notched Izod Impact (23°C, 6.40 mm)	390	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 12.7 mm	92.0	°C	ASTM D648
1.8 MPa, Unannealed	81.0	°C	ISO 75-2/A
Vicat Softening Temperature	97.0	°C	ISO 306/B50
CLTE - Flow	7.0E-5	cm/cm/°C	ISO 11359-2
Flammability	Nominal Value	Test Method	
Flame Rating		UL 94	
1.50 mm	V-0		
2.00 mm	5VB		
2.50 mm	5VA		
Injection	Nominal Value	Unit	
Drying Temperature	85.0 to 90.0	°C	
Drying Time	3.0 to 4.0	hr	
Rear Temperature	190 to 210	°C	
Middle Temperature	210 to 230	°C	
Front Temperature	230 to 250	°C	
Nozzle Temperature	220 to 250	°C	
Mold Temperature	40.0 to 60.0	°C	
Back Pressure	5.00 to 15.0	MPa	

Screw Speed

40 to 60

rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

