

Lucky Enpla LGF1101F

Polycarbonate
Lucky Enpla Co LTD

Message:

Lucky Enpla LGF1101F is a polycarbonate (PC) product that contains 10% glass fiber reinforced materials. It can be processed by injection molding and is available in North America, Europe or the Asia-Pacific region. Typical application areas are: electrical/electronic applications.
Features include:
flame retardant/rated flame
Halogen-free

General Information			
UL YellowCard	E217401-524084		
Filler / Reinforcement	Glass fiber reinforced material, 10% filler by weight		
Features	Halogen-free		
Uses	Electrical/Electronic Applications		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.20 - 0.40	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	76.5	MPa	ASTM D638
Flexural Modulus ²	3820	MPa	ASTM D790
Flexural Strength ³	123	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (3.18 mm)	78	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	138	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	70.0 - 90.0	°C	
Drying Time	2.0 - 3.0	hr	
Rear Temperature	290 - 310	°C	
Middle Temperature	290 - 310	°C	
Front Temperature	290 - 310	°C	
Nozzle Temperature	280 - 310	°C	
Mold Temperature	90.0 - 110	°C	
Back Pressure	1.96 - 3.92	MPa	
Screw Speed	60 - 80	rpm	
Injection instructions			
Resin Temperature: 290-310°CInjection Pressure (1st Pressure): 700-1200 kg/cm²Injection Pressure (2nd Pressure): 400-800 kg/cm²			

NOTE

1.	10 mm/min
2.	5.0 mm/min
3.	5.0 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

