

Borealis PE BB2541

High Density Polyethylene

Borealis AG

Message:

BB2541 is a high density polyethylene with very high ESCR This product is intended for blow moulding.

General Information			
Features	High ESCR (Stress Crack Resist.)		
	Recyclable Material		
Uses	Blow Molding Applications		
	Bottles		
	Containers		
Processing Method	Blow Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.954	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR)			ISO 1133
190°C/2.16 kg	0.30	g/10 min	
190°C/21.6 kg	32	g/10 min	
190°C/5.0 kg	1.5	g/10 min	
Environmental Stress-Cracking Resistance (10% Antarox, F50)	500	hr	ASTM D1693A
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	64		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1100	MPa	ISO 527-2
Tensile Stress (Yield)	25.0	MPa	ISO 527-2/50
Tensile Strain (Yield)	9.0	%	ISO 527-2/50
Flexural Modulus ¹	1200	MPa	ISO 178
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	75.0	°C	ISO 75-2/B
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	170 to 190	°C	
Cylinder Zone 2 Temp.	170 to 190	°C	
Cylinder Zone 3 Temp.	170 to 190	°C	
Cylinder Zone 4 Temp.	170 to 190	°C	
Cylinder Zone 5 Temp.	170 to 190	°C	
Melt Temperature	170 to 200	°C	
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

