

EPO-TEK® H20E-SLR-HVMX

Epoxy; Epoxide

Epoxy Technology Inc.

Message:

EPO-TEK® H20E-SLR-HVMX is a two-component, electrically conductive, epoxy for meter mix dispensing applications. It is designed for solar ribbon bonding of photovoltaic modules. It provides the electrical back-contact for ribbon stringing of solar cells into modules and panels. It is a higher viscosity version of EPO-TEK H20E-SLR-MX.

General Information		
Features	Electrically Conductive	
	Fast Cure	
	Thixotropic	
Uses	Adhesives	
	Electrical/Electronic Applications	
	Solar Panels	
Agency Ratings	EC 1907/2006 (REACH)	
	EU 2003/11/EC	
	EU 2006/122/EC	
RoHS Compliance	RoHS Compliant	
Forms	Paste	
Physical	Nominal Value	Unit
Particle Size	< 20.0	µm
Degradation Temperature	400	°C
Die Shear Strength - > 10 kg (23°C)	23.4	MPa
Operating Temperature		
Continuous	-55 to 200	°C
Intermittent	-55 to 300	°C
Storage Modulus	6.11	GPa
Thixotropic Index	3.51	
Weight Loss on Heating		
200°C	0.36	%
250°C	1.3	%
300°C	2.4	%
Thermal	Nominal Value	Unit
Glass Transition Temperature ¹	88.0	°C
CLTE - Flow		
-- ²	5.1E-5	cm/cm/°C
-- ³	2.6E-4	cm/cm/°C

Thermal Conductivity	1.5	W/m/K
Thermoset	Nominal Value	Unit
Thermoset Components		
Part A	Mix Ratio by Weight: 100	
Part B	Mix Ratio by Weight: 11	
Shelf Life (23°C)	52	wk
Uncured Properties	Nominal Value	Unit
Color		
-- 4	Amber	
-- 5	Silver	
Density		
Part B	1.10	g/cm³
Part A	2.60	g/cm³
Viscosity ⁶ (23°C)	7.2	Pa·s
Curing Time (140°C)	0.17	hr
Pot Life	1100	min
Cured Properties	Nominal Value	Unit
Shore Hardness (Shore D)	55	
Lap Shear Strength (23°C)	12.7	MPa
Volume Resistivity (23°C)	< 4.0E-3	ohms·cm
NOTE		
1.	Dynamic Cure 20-200°C/ISO 25 Min; Ramp -10-200°C @ 20°C/Min	
2.	Below Tg	
3.	Above Tg	
4.	Part B	
5.	Part A	
6.	50 rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT