

Cellidor B 531-07S

Cellulose Acetate Butyrate

ALBIS PLASTIC GmbH

Message:

Cellidor B 531-07S is a Cellulose Acetate Butyrate (CAB) product. It is available in Asia Pacific, Europe, or North America.

Characteristics include:

REACH Compliant

RoHS Compliant

Plasticized

Eco-Friendly/Green

General Information			
Additive	Plasticizer (7%)		
Features	Non-Phthalate Plasticizer		
	Renewable Resource Content		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (210°C/2.16 kg)	5.00	cm³/10min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 132/30)	75.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1700	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Yield	42.0	MPa	
Break	40.0	MPa	
Tensile Strain (Break)	15	%	ISO 527-2
Flexural Stress (3.5% Strain)	52.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	13	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	92.0	°C	ISO 75-2/A
Vicat Softening Temperature	95.0	°C	ISO 306/B50
Injection	Nominal Value	Unit	
Drying Temperature	60.0 to 90.0	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.050	%	

Extrusion	Nominal Value	Unit
Melt Temperature	180 to 230	°C
Die Temperature	40.0 to 80.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

