

Polymist® XPP 515-S

Polytetrafluoroethylene

Solvay Specialty Polymers

Message:

Polymist® 515-S a white PTFE micronized powder PTFE micronized powder composed of discrete particles.

Designed for use in critical engineering and high end performance plastics applications, Polymist® XPP 515-S will improve wear resistance and low coefficient of friction.

Main features of Polymist® 515-S are:

Improved wear resistance

Increased pressure x velocity (PV) limits

Reduced friction and stick-slip response

General Information			
Uses	Additive		
Appearance	White		
Forms	Powder		
Physical	Nominal Value	Unit	Test Method
Specific surface area	3.0	m ² /g	Internal method
Particle size-(d50)	20.0	µm	Internal method
Volume density	400	g/l	ASTM D4895
Melt Temperature	320 - 330	°C	ASTM D3418
Additional Information	Nominal Value	Unit	Test Method

ProcessingPolymist® XPP 515-S can be used in a wide variety of different thermoplastics. Typical loadings are 5 - 20% by weight of the compound and the optimum loading is dependent by the resin type and the desired final properties of the part.Besides its main function as a friction and wear additive, Polymist® XPP 515-S micronized powders can be also used at lower concentration to provide the following properties:

Processing aid to improve compounding and molding conditions

Mold release agent due to non-stick properties

Polymist® XPP 515-S micronized PTFE can be incorporated into thermoplastics by pre-mixing or co-feeding with the base polymer using standard industrial equipment and technology. The compound can also be prepared by first using a masterbatch.Storage and Handling

The usual precautions for safe storage and handling of Polymist® XPP 515-S should be taken according to material safety documentation and experience. There will be no chemical deterioration of the Polymist® XPP 515-S during proper storage.

Shelf life of Polymist® XPP 515-S micronized powders will vary depending upon whether the recommended storage conditions are maintained and whether the material remains free from foreign contamination during storage time (not exposed to dirt, dust, water or other chemicals). The material should remain sealed in the original containers and storage conditions should provide for protection from temperature extremes as well as rain, snow or other wet environments (or such conditions which may damage the storage containers in which the product is stored).

Safety and Toxicology

Before using PTFE Polymist® XPP 515-S micronized powders consult the product Material Safety Data Sheet and follow all label directions and handling precautions.

As with all PTFE materials, handling and processing should only be carried out in well ventilated areas. Vapor extractor units should be installed above processing equipment. Fumes must not be inhaled and eye and skin contact ought to be avoided. In case of skin contact wash with soap and water. In case of eye contact flush with water immediately and seek medical help. Do not smoke in areas contaminated with powder, vapor or fumes. See

Material Safety Data Sheet for detailed advice on waste disposal methods.

Packaging

Polymist® XPP 515-S is packaged in 25 kg non returnable drums. Each drum has one bag liner made of polyethylene resin.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

