

# SEPAZ™ LH50

Polypropylene Homopolymer  
Mando Advanced Materials Co., Ltd.

Message:

SEPAZ™ LH50 is a Polypropylene Homopolymer (PP Homopolymer) product filled with 50% long glass fiber. It is available in Asia Pacific. Primary characteristic: flame rated.

General Information			
Filler / Reinforcement	Long Glass Fiber,50% Filler by Weight		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.33	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage <sup>1</sup>			ASTM D955
Flow	0.20	%	
Across Flow	0.50	%	
Water Absorption (24 hr)	0.020	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	132	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	10300	MPa	ASTM D790
Flexural Strength	206	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	260	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	165	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	220 to 230	°C	
Mold Temperature	40.0 to 70.0	°C	
NOTE			

1. 60°C Mold Temperature

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533

Email: [sales@su-jiao.com](mailto:sales@su-jiao.com)

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

