

Premi-Glas® 1268

Thermoset, Unspecified

Premix, Inc.

Message:

Premi-Glas® 1266 is a fiberglass reinforced thermoset Thick Molding Compound for composite powertrain applications such as valve covers and timing gear covers.

General Information			
Filler / Reinforcement	Glass Fiber		
Features	Good Chemical Resistance		
	Salt Water/Spray Resistant		
Uses	Metal Replacement		
Forms	TMC - Thick Molding Compound		
Processing Method	Compression Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.74	g/cm ³	
Molding Shrinkage - Flow	0.080	%	
Water Absorption (Saturation, 23°C)	0.10	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	10000	MPa	ISO 527-2
Tensile Stress (Break)	37.0	MPa	ISO 527-2
Flexural Modulus - Tangent	9200	MPa	ISO 178
Flexural Stress	82.0	MPa	ISO 178
Poisson's Ratio	0.35		
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact Strength	10	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	> 270	°C	ISO 75-2/A
Glass Transition Temperature	177	°C	ASTM D4065
CLTE			
Flow ¹	2.5E-5	cm/cm/°C	
Transverse ²	3.5E-5	cm/cm/°C	
Thermal Conductivity	0.48	W/m/K	
Injection	Nominal Value	Unit	
Mold Temperature	160	°C	
Injection Pressure	6.89	MPa	
NOTE			
1.	XY Direction		
2.	Z Direction		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

