

# SLOVAMID® 66/6 GF 20

Polyamide 66/6 Copolymer

Plastcom

## Message:

Chemically reinforced alloy PA 66 and PA 6 with 20 % glass fibre, suitable for mouldings with high strength and toughness also at minus temperatures. Used in the automotive, engineering and electrical industry. Application: hobby tools, covers of electrottools, electromotors, cooling screws of blowers, gear wheels, carrying parts in the automotive industry like eg. brake cables. Delivered in natural mode and in the full RAL colour scale.

| General Information                        |                                    |                   |             |
|--|------------------------------------|-------------------|-------------|
| Filler / Reinforcement                     | Glass Fiber,20% Filler by Weight   |                   |             |
| Features                                   | Chemically Coupled                 |                   |             |
|  | High Strength                      |                   |             |
|  | Low Temperature Toughness          |                   |             |
|  | Ultra High Toughness               |                   |             |
| Uses                                       | Automotive Applications            |                   |             |
|  | Electrical/Electronic Applications |                   |             |
|  | Engineering Parts                  |                   |             |
|  | Gears                              |                   |             |
|  | Power/Other Tools                  |                   |             |
| Appearance                                 | Colors Available                   |                   |             |
|  | Natural Color                      |                   |             |
| Processing Method                          | Injection Molding                  |                   |             |
| Physical                                   | Nominal Value                      | Unit              | Test Method |
| Density                                    | 1.32                               | g/cm <sup>3</sup> | ISO 1183    |
| Melt Mass-Flow Rate (MFR) (275°C/0.325 kg) | 3.0                                | g/10 min          | ISO 1133    |
| Molding Shrinkage                          |                                    |                   | STM 64 0808 |
| Across Flow                                | 0.19                               | %                 |             |
| Flow                                       | 0.79                               | %                 |             |
| Water Content                              | 0.15                               | %                 | ISO 960     |
| Mechanical                                 | Nominal Value                      | Unit              | Test Method |
| Tensile Modulus                            | 7000                               | MPa               | ISO 527-2   |
| Tensile Stress (Yield)                     | 135                                | MPa               | ISO 527-2   |
| Tensile Strain (Yield)                     | 3.0                                | %                 | ISO 527-2   |
| Flexural Modulus                           | 6000                               | MPa               | ISO 178     |
| Flexural Stress                            | 200                                | MPa               | ISO 178     |
| Impact                                     | Nominal Value                      | Unit              | Test Method |
| Charpy Notched Impact Strength             |                                    |                   | ISO 179     |

| -20°C  | 8.0           | kJ/m <sup>2</sup> |                |
|--|---------------|-------------------|----------------|
| 23°C   | 9.0           | kJ/m <sup>2</sup> |                |
| Charpy Unnotched Impact Strength                   |               |                   | ISO 179        |
| -20°C  | 45            | kJ/m <sup>2</sup> |                |
| 23°C   | 50            | kJ/m <sup>2</sup> |                |
| Thermal  | Nominal Value | Unit              | Test Method    |
| Heat Deflection Temperature (0.45 MPa, Unannealed) | 250           | °C                | ISO 75-2/B     |
| Vicat Softening Temperature                        | 250           | °C                | ISO 306/B      |
| Melting Temperature (DSC)                          | 260           | °C                | ISO 3146       |
| Flammability                                       | Nominal Value | Unit              | Test Method    |
| Flame Rating                                       | HB            |                   | UL 94          |
| Glow Wire Ignition Temperature                     | 650           | °C                | IEC 60695-2-13 |
| Injection  | Nominal Value | Unit              |                |
| Drying Temperature                                 | 80.0          | °C                |                |
| Drying Time  | 4.0           | hr                |                |
| Processing (Melt) Temp                             | 280 to 300    | °C                |                |
| Mold Temperature                                   | 60.0 to 90.0  | °C                |                |
| Injection Pressure                                 | 70.0 to 120   | MPa               |                |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

