Unigel PS U288

General Purpose Polystyrene **Unigel Plásticos**

Message:

Excellent gloss and transparency properties.

Excellent dimensional stability.

Suitable for extrusion of transparent sheets and in blends with high impact polystyrene.

Approved for food contact

General Information			
Features	Food Contact Acceptable		
	Good Dimensional Stability		
	High Clarity		
	High Gloss		
Uses	Blending		
	Sheet		
Agency Ratings	FDA 21 CFR 177.1640		
Appearance	Clear/Transparent		
Processing Method	Sheet Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	4.3	g/10 min	ASTM D1238
Water Absorption (Equilibrium)	0.030	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2800	MPa	ASTM D638
Tensile Strength (Break)	46.0	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.50 mm)	19	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.30 mm)	81.0	°C	ASTM D648
Vicat Softening Temperature	96.0	°C	ASTM D1525 ¹
Flammability	Nominal Value		Test Method
Flame Rating	НВ		UL 94
NOTE			
1.	Rate A (50°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



Page 2