TABOREX TA 1134 HD

High Density Polyethylene

SILON s.ro

Message:

A chemically-crosslinkable HDPE compound for the production of pipes for domestic hot and cold water, under floor heating and central heating application.

TA 1134 HD is a crosslinkable compound made by Silane grafted ethylene polymer. This graft polymer constitutes together with a Masterbatch containing the crosslinking catalyst a "SIOPLAS-SYSTEM". Pipes produced with the SILON grade TA 1134 HD fulfil the requirements of ASTM F876-99a, ASTM F877-99a, CSA 137.5-99, DIN 16892, BS 7291 and all related standards.

This system allows the compound to be extruded as a normal thermoplastic polymer, which will attain a high level of crosslinking in the processed form. The final product has all the improved properties associated with crosslinked polyethylene.

General Information			
Features	Crosslinkable		
Uses	Piping system		
Forms	Sphere		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.943	g/cm³	DIN 53479, ASTM D1505
Apparent Density	0.55	g/cm³	DIN 53466
Melt Mass-Flow Rate (MFR) (190°C/5.0 kg)	2.5	g/10 min	Internal method
Moisture Content		%	Internal method
Volatile Matter		%	Internal method
Gel Content ¹	70	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	19.0	МРа	ISO 527-2
Tensile Strain (Break)	250	%	ISO 527-2
Extrusion	Nominal Value	Unit	
Drying Temperature	80.0 - 90.0	°C	
Drying Time	2.0	hr	
Cylinder Zone 1 Temp.	160 - 170	°C	
Cylinder Zone 2 Temp.	170 - 180	°C	
Cylinder Zone 3 Temp.	170 - 190	°C	
Cylinder Zone 4 Temp.	170 - 190	°C	
Die Temperature	190 - 220	°C	
Extrusion instructions			
L/D: >25Compression ratio: 3:1 to 2.5 : 1Hea	d: 200 to 210°CScrew: 70°C to	o 90 °C	

DIN 16892/ ASTM F 876-99a

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

