

Elvaloy® HP662

Thermoplastic

DuPont Packaging & Industrial Polymers

Message:

DuPont™ Elvaloy® HP662 is a ethylene terpolymer, which is most commonly used as a modifier for a variety of other polymers.

E/nBA/CO = ethylene/n-butyl acrylate/carbon monoxide

General Information			
Uses	Plastics Modification		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.960	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	25	g/10 min	ASTM D1238, ISO 1133
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	69		ASTM D2240, ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			
Break	3.40	MPa	ISO 527-2
--	3.40	MPa	ASTM D638
Tensile Elongation (Break)	1100	%	ASTM D638, ISO 527-2
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature ¹	-54.0	°C	ASTM E1356
Peak Melting Temperature	62.0	°C	ASTM D3418, ISO 3146

NOTE

1. loss modulus peak at 1 hz

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

