

Arnite® A06 700

Polyethylene Terephthalate
DSM Engineering Plastics

Message:

Arnite® A06 700 is a Polyethylene Terephthalate (PET) material. It is available in Europe for extrusion.
Important attributes of Arnite® A06 700 are:
High Viscosity
Impact Resistant

General Information			
Features	Good Impact Resistance		
	Ultra High Viscosity		
Forms	Pellets		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.40	g/cm ³	ISO 1183
Water Absorption (Equilibrium, 23°C, 50% RH)	0.30	%	ISO 62
Thermal	Nominal Value	Unit	Test Method
Melting Temperature ¹	255	°C	ISO 11357-3
Fill Analysis	Nominal Value	Unit	Test Method
Melt Thermal Conductivity	0.21	W/m/K	
Specific Heat Capacity of Melt	2.050	kJ/kg/K	
RSV ²	2.10		Internal Method
Injection	Nominal Value	Unit	
Drying Temperature	100 to 120	°C	
Drying Time	3.0 to 12	hr	
Rear Temperature	270 to 280	°C	
Middle Temperature	270 to 290	°C	
Front Temperature	270 to 290	°C	
Nozzle Temperature	270 to 290	°C	
Processing (Melt) Temp	270 to 290	°C	
Mold Temperature	130 to 140	°C	
Injection Rate	Moderate-Fast		
Back Pressure	3.00 to 10.0	MPa	
Screw Compression Ratio	2.5:1.0		
NOTE			
1.	10°C/min		
2.	m-cresol, 1g/100ml		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

