NuSil EPM-2401

Silicone

NuSil Technology

Message:

As a low stress alternative for electronic packaging, NuSil Technology's silicones allow the designer to choose from a unique line of silicones for various levels of packaging. We have an extensive line of encapsulants, adhesives, and greases to choose from. These include thermally and electrically conductive silicones for Thermal Interface Materials (TIM) or for EMI and RFI shielding applications. Benefits of Silicone for Electronics: Wide Operating Temperature Range of -115 °C to 250 °C Low moisture absorption, < 0.4% Typical **Corrosion Resistance** High Dielectric Strength > 500 V/mil (0.001 inch) or 20 kV/mm Fillers can be added to provide thermal and electrical conductive properties Low Modulus (Typically less than 5.5 MPa/800 psi) Stable chemical and mechanical properties when exposed to high temperatures Low Shrinkage Available as gels, elastomers, film adhesives sheeting, and greases General Purpose: Thermal Interface Materials (TIMs) Comments: 0.70 W/m-K, BLT <0.5 µn, Zinc filled General Information

Good Corrosion Resistance	-
Good Thermal Stability	
Low Moisture Absorption	
Low Shrinkage	
Thermally Conductive	
	Good Thermal Stability Low Moisture Absorption Low Shrinkage

Uses	Electrical/Electronic Applications		
Thermal	Nominal Value	Unit	Test Method
Thermal Conductivity	0.70	W/m/K	ASTM E1530
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Additional Information	Nominal Value	Unit	
Ionic Content			
CI	< 5	ppm	
К	< 2	ppm	
Na	< 4	ppm	
Operating Temperature	-40 to 200	°C	
Uncured Properties	Nominal Value	Unit	
Color	White		
Density	2.29	g/cm³	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

