

Starex TF-0957H

Polymethyl Methacrylate Acrylic
LOTTE ADVANCED MATERIALS CO., LTD.

Message:

Starex TF-0957H is a polymethyl methacrylate-acrylic acid product. It is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Typical application areas are: electrical appliances.

General Information			
UL YellowCard	E115797-100039316		
Features	General		
Uses	Electrical appliances		
Physical	Nominal Value	Unit	Test Method
Specific Gravity (Natural)	1.17	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	16	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			
Flow: 3.20mm	0.40	%	ASTM D955
Transverse flow: 3.20mm	0.40	%	ASTM D955
Lateral flow: 3.20mm	0.40	%	ISO 2577
Traffic: 3.20mm	0.40	%	ISO 2577
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			
Class r	108		ASTM D785
R scale	108		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2000	MPa	ASTM D638
--	2000	MPa	ISO 527-2/5
Tensile Strength			
Yield ²	44.0	MPa	ASTM D638
Yield	45.0	MPa	ISO 527-2/5
Fracture ³	44.0	MPa	ASTM D638
Fracture	50.0	MPa	ISO 527-2/5
Tensile Elongation			
Fracture ⁴	40	%	ASTM D638
Fracture	15	%	ISO 527-2/5
Flexural Modulus			
-- ⁵	1900	MPa	ASTM D790
-- ⁶	1900	MPa	ISO 178
Flexural Strength			
-- ⁷	68.0	MPa	ASTM D790

-- 8	70.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹ (23°C)	2.0	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
23°C, 3.18 mm	49	J/m	ASTM D256
23°C, 6.35 mm	49	J/m	ASTM D256
23°C ¹⁰	2.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 6.40mm	80.0	°C	ASTM D648
0.45 MPa, unannealed, 4.00mm	75.0	°C	ISO 75-2/B
1.8 MPa, unannealed, 6.40mm	75.0	°C	ASTM D648
1.8 MPa, not annealed, 4.00mm	70.0	°C	ISO 75-2/A
	85.0		
Vicat Softening Temperature	86.0	°C	ISO 306/B50
Optical	Nominal Value	Unit	Test Method
Haze			
3200 μm	1.7	%	ASTM D1003
3200 μm	1.7	%	ISO 13468
NOTE			
1.	5.0 mm/min		
2.	5.0 mm/min		
3.	5.0 mm/min		
4.	5.0 mm/min		
5.	2.8 mm/min		
6.	2.0 mm/min		
7.	2.8 mm/min		
8.	2.0 mm/min		
9.	Thickness: 4mm		
10.	Thickness: 4mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT