COSMOTHENE® G810-S

Low Density Polyethylene

TPC, The Polyolefin Company (Singapore) Pte Ltd

Message:

COSMOTHENE® G810-S is a Low Density Polyethylene product. It can be processed by injection molding and is available in Asia Pacific.

Characteristics include:

Good Flexibility

Good Processability

High ESCR (Stress Crack Resistant)

| General Information | | | |
|----------------------------|----------------------------------|----------|-------------|
| Features | Good Flexibility | | |
| | Good Moldability | | |
| | High ESCR (Stress Crack Resist.) | | |
| | | | |
| Forms | Pellets | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 0.918 | g/cm³ | ASTM D792 |
| Melt Mass-Flow Rate (MFR) | 35 | g/10 min | ASTM D1238 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Break) | 9.81 | МРа | ASTM D638 |
| Tensile Elongation (Break) | 600 | % | ASTM D638 |
| Apparent Bending Modulus | 157 | MPa | ASTM D747 |
| Thermal | Nominal Value | Unit | |
| Melting Temperature | 105 | °C | |
| Injection | Nominal Value | Unit | |
| Processing (Melt) Temp | 170 to 200 | °C | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

