# ETILINAS HD3840UA

### Medium Density Polyethylene

#### POLYETHYLENE MALAYSIA SDN BHD

#### Message:

ETILINAS HD3840UA is a ultra-violet (UV) light stabilised linear medium density polyethylene grade with a narrow molecular weight distribution, supplied in pellet form for use as a rotational moulding grade.

Characteristics include: good impact strength, excellent external and internal surface finish, and is UV stabilized.

Applications include: rotational moulded items, and injection moulded technical parts and closures.

General Information			
Additive	UV stabilizer		
Features	Impact resistance, good		
	Excellent appearance		
	Narrow molecular weight distribution		
Uses	Engineering accessories		
	Shell		
Forms	Particle		
Processing Method	rotomolding		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (190°C/2.16			
kg)	4.0	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	62		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	16.0	MPa	ISO 527-2/2
Tensile Strain (Break)	200	%	ISO 527-2/2
Flexural Modulus	650	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength	20	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	117	°C	ISO 306/A
Melting Temperature (DSC)	125	°C	ISO 3146
CLTE - Flow	1.0E-3	cm/cm/°C	ASTM D696
Thermal Conductivity	0.48	W/m/K	ASTM C177
Additional Information			

Density, ISO 1872/1, Annealed: 938 kg/m<sup>3</sup>

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

