

Hostacom HRC 181L W92341

Polypropylene Homopolymer

LyondellBasell Industries

Message:

Hostacom HRC 181L W92341 is a mineral filled PP homopolymer, with medium melt flow rate. Product is UL listed. This grade is not intended for medical, pharmaceutical, food and drinking water applications.

General Information			
Filler / Reinforcement	Mineral filler		
Features	Homopolymer		
	Medium liquidity		
Uses	Electrical appliances		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.21	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	11	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	3800	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	32.0	MPa	ISO 527-2
Tensile Strain (Yield, 23°C)	3.0	%	ISO 527-2
Flexural Modulus ¹ (23°C)	4100	MPa	ISO 178/A
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	2.2	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	18	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	125	°C	ISO 75-2/B
1.8 MPa, not annealed	75.0	°C	ISO 75-2/A
NOTE			
1.	1.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

