

Niche PA66GF13N

Polyamide 66

Niche Polymer, LLC

Message:

Niche PA66GF13N is a Polyamide 66 (Nylon 66) material filled with 13% glass fiber. It is available in North America.

| General Information | | | |
|---------------------------------------------------------|----------------------------------|------|-------------|
| Filler / Reinforcement | Glass Fiber,13% Filler by Weight | | |
| Appearance | Natural Color | | |
| Physical | Nominal Value | Unit | Test Method |
| Molding Shrinkage - Flow | 0.55 | % | ASTM D955 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Break) | 106 | MPa | ASTM D638 |
| Tensile Elongation (Break) | 3.5 | % | ASTM D638 |
| Flexural Modulus | 4830 | MPa | ASTM D790 |
| Flexural Strength | 171 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Unnotched Izod Impact (23°C, 3.18 mm) | 190 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (1.8 MPa, Unannealed) | 227 | °C | ASTM D648 |
| Melting Temperature | 254 to 266 | °C | ASTM D789 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT