

BJB Polyurethane TC-892 A/B

Polyurethane
BJB Enterprises, Inc.

Message:

TC-892 A/B incorporates a non-mercury based catalyst system that produces a tough 80 shore D material with a 20-minute work time. This system can be used to hand pour large electronic housing, models of all kinds, and point of purchase items. This system is also available in a 5-minute work time (TC-890), and a 12-minute work time (TC-891).

Product Highlights:

Non-mercury

Convenient mixing ratio: 1 to 1 parts by weight

Long working time: 20 minutes

Low viscosity, flows easily

Demold time: 5-6 hours at ambient temperature in silicone rubber mold (1/8" thick section).

General Information			
Features	Good Flow		
	Low Viscosity		
Uses	Electrical Housing		
	Electrical/Electronic Applications		
RoHS Compliance	RoHS Compliant		
Appearance	Opaque		
	White		
Forms	Liquid		
Processing Method	Casting		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14	g/cm ³	ASTM D792
Specific Gravity			
Part A	1.177	g/cm ³	
Part B	1.037	g/cm ³	
Shrinkage (1.27 cm)	0.50	%	
Gel Time	25.0	min	
Work Time (25°C)	20.0	min	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	78 to 82		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1650	MPa	ASTM D638
Tensile Strength	52.4	MPa	ASTM D638
Tensile Elongation (Break)	10	%	ASTM D638
Flexural Modulus	1720	MPa	ASTM D790
Flexural Strength	68.9	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	37	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	90.6	°C	
1.8 MPa, Unannealed	80.6	°C	
Thermoset	Nominal Value	Unit	
Thermoset Components			
Part A	Mix Ratio by Weight: 100, Mix Ratio by Volume: 88		
Part B	Mix Ratio by Weight: 100, Mix Ratio by Volume: 100		
Shelf Life	26	wk	
Thermoset Mix Viscosity			
25°C ¹	325	cP	
25°C ²	830	cP	
25°C	725	cP	
Demold Time (25°C)	300 to 360	min	
Post Cure Time (82°C)	16	hr	
NOTE			
1.	Part A		
2.	Part B		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

