

# 3M™ Dyneon™ Fluoroelastomer FE 5620N

Fluoroelastomer

3M Advanced Materials Division

Message:

3M™ Dyneon™ Fluoroelastomer FE 5620N is a dipolymer made from hexafluoropropylene and vinylidene fluoride. FE 5620N has an incorporated bisphenol cure system.

Special Features

Composition: dipolymer of vinylidene fluoride and hexafluoropropylene

Process targets: injection and transfer moulding, extrusion and calendering

Proprietary incorporated cure technology

Improved cure technology resulting in more consistent part size from successive moulding cycles

Low viscosity version of 3M™ Dyneon™ Fluoroelastomer FE 5640Q

Improved scorch resistance at high moulding temperatures

Excellent mould release - can be used in automated injection moulding equipment

Clean running

Compounds prepared from Dyneon FE 5620N can be formulated to meet Mil-R-83248

Typical Applications

3M™ Dyneon™ Fluoroelastomer FE 5620N is suitable to produce O-rings in an injection moulding process.

General Information			
Features	Low viscosity		
	Good demoulding performance		
Uses	O-rings		
Agency Ratings	MIL R-83248		
Appearance	Opacity		
	White-like		
Forms	Thick sheet		
Processing Method	Extrusion		
	Resin transfer molding		
	Calendering		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.80	g/cm <sup>3</sup>	Internal method
Mooney Viscosity (ML 1+10, 121°C)	23	MU	Internal method
Fluorine Content	66	%	Internal method
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	77		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress <sup>1</sup> (100% Strain)	6.00	MPa	ASTM D412A
Tensile Strength <sup>2</sup>	16.5	MPa	ASTM D412A
Tensile Elongation <sup>3</sup> (Break)	210	%	ASTM D412A

Compression Set			ASTM D1414
200°C, 70 hr <sup>4</sup>	14	%	ASTM D1414
200°C, 70 hr <sup>5</sup>	12	%	ASTM D1414

NOTE			
1.	D mould		
2.	Die D		
3.	D mould		
4.	Post cured 16 hours @ 230°C		
5.	Post cured 24 hours @ 260°C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

