

# Osterlene® PPR75CLNX

Polypropylene Random Copolymer

Osterman & Company

Message:

PPR75CLNX is a clarified random copolymer specially designed and formulated for clear injection molding applications and is formulated with antistat and lube for excellent mold release and material handling. This resin is best suited for injection molding applications.

Applications for PPR75CLNX include housewares and clear containers.

Osterlene PPR75CLNX meets the requirements of the Food and Drug Administration, 21 CFR Section 177.1520. This regulation allows the use of this olefin polymer in "...articles or components of articles intended for use in contact with food." Specific limitations may apply. Contact your Osterman sales representative for more information.

General Information			
Features	Antistatic property		
	Definition, high		
	Compliance of Food Exposure		
	Good demoulding performance		
	Random copolymer		
Uses	Household goods		
	Container		
Agency Ratings	FDA 21 CFR 177.1520		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	75	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Yield)	27.6	MPa	ASTM D638
Tensile Elongation (Yield)	13	%	ASTM D638
Flexural Modulus - 1% Secant <sup>2</sup>	1030	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	53	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	85.0	°C	ASTM D648
NOTE			
1.	50 mm/min		
2.	1.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT