

# ECP 2310

Acrylonitrile Butadiene Styrene  
TBA Electro Conductive Products Ltd.

## Message:

The new ECP 2000 series of static dissipative polymers have been formulated specifically for clean room environments where low offgassing, low particulate, contamination and washability are required. The compounds can be coloured.

The materials are permanently conductive and can be processed on conventional equipment. The products are humidity independent, aqueous washable and can be re-used.

Applications that are ideally suited for the compounds and in use commercially at customer sites include: packaging for electronic components, medical device packaging, in-process carriers, fixturing devices, chip rails, vacuum tubing and business machine components.

Because of their flexibility, the thermoplastic polyurethane (TPU) based alloys are also useful as softwall cleanroom materials, flexible packaging, hose and tubing, floor and table mats and other flexible cleanroom applications.

General Information	
Features	Conductive
	Good Colorability
	Good Flexibility
	Humidity Independent
Uses	Business Equipment
	Medical Packaging
	Packaging
	Tubing
Appearance	Translucent
Processing Method	Injection Molding
	Thermoforming

Physical	Nominal Value	Unit
Density	1.08	g/cm <sup>3</sup>
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min
Mechanical	Nominal Value	Unit
Tensile Modulus	1300	MPa
Tensile Stress	23.0	MPa
Electrical	Nominal Value	Unit
Surface Resistivity	1.0E+10	ohms

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

